



TC Mirafi

TECHNICAL DATA SHEET

Mirafi 600X

Mirafi 600X is composed of high-tenacity polypropylene yarns, which are woven into a stable network such that the yarns retain their relative position. 600X is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value	
			MD	CD
Wide Width Tensile Strength	ASTM D 4595	kN/m (lbs/in)	30.6 (175)	30.6 (175)
Grab Tensile Strength	ASTM D 4632	kN (lbs)	1.40 (315)	1.40 (315)
Grab Tensile Elongation	ASTM D 4632	%	15	10
Trapezoid Tear Strength	ASTM D 4533	kN (lbs)	0.53 (120)	0.53 (120)
Mullen Burst Strength	ASTM D 3786	kPa (psi)	4134 (600)	
Puncture Strength	ASTM D 4833	kN (lbs)	0.53 (120)	
Percent Open Area	COE-02215-86	%	1	
Apparent Opening Size (AOS)	ASTM D 4751	mm (U.S. Sieve)	0.425 (40)	
Permittivity	ASTM D 4491	sec ⁻¹	0.05	
Flow Rate	ASTM D 4491	l/min/m ² (gal/min/ft ²)	163 (4.0)	
UV Resistance (at 500 hours)	ASTM D 4355	% strength retained	70	

Physical Properties	Test Method	Unit	Typical Value	
Weight	ASTM D 5261	g/m ² (oz/yd ²)	203 (6.0)	
Thickness	ASTM D 5199	mm (mils)	0.64 (25)	
Roll Dimensions (width x length)	--	m (ft)	3.8 x 110 (12.5 x 360)	5.5 x 76 (18 x 250)
Roll Area	--	m ² (yd ²)	418 (500)	418 (500)
Estimated Roll Weight	--	kg (lb)	109 (240)	109 (240)

DISCLAIMER: TC Mirafi warrants our products to be free from defects in material and workmanship when delivered to TC Mirafi's customers and that our products meet our published specifications. Contact your local TC Mirafi Representative for detailed product specification and warranty information.